

# Electrochemical Co-deposition of Nickel Oxide and Polyaniline

Xu-Yuan Peng<sup>a</sup>, Xiao-Xia Liu<sup>a,\*</sup>, Pei-Jie Hua<sup>a</sup>, Dermot Diamond<sup>b</sup>, King-Tong Lau<sup>b,#</sup>

<sup>a</sup> China-Ireland Center for Advanced Materials and Sensor Development, Department of Chemistry, Northeastern University, Shenyang, 110004, China

<sup>b</sup> China-Ireland Center for Advanced Materials and Sensor Development, National Centre for Sensor Research, Dublin City University, Glasnevin, Dublin 9, Ireland

Correspondence: \*[xxliu@mail.neu.edu.cn](mailto:xxliu@mail.neu.edu.cn), Tel: +862483683642, fax: 862423600159  
#[Kim.lau@dcu.ie](mailto:Kim.lau@dcu.ie), Tel: +35317006008, Fax: +35317007995

## ABSTRACT

Nickel oxide (NiO<sub>x</sub>) and polyaniline (PAni) were electro-co-deposited from NiSO<sub>4</sub> and aniline through cyclic voltammetric scans to afford PAni-NiO<sub>x</sub> composite film at controlled pH environment. The electrochemical activities of the film were investigated by cyclic voltammetry in 0.1 M NaOH and 0.1 M H<sub>2</sub>SO<sub>4</sub>, respectively. Typical redox couples of PAni in 0.1 M H<sub>2</sub>SO<sub>4</sub> appeared at *ca.* 0.2 V and 0.4 V *vs.* SCE; Ni(II) / Ni(III) redox couple was observed at *ca.* 0.4 V *vs.* SCE in 0.1 M NaOH. The morphologies and elemental components of the films were inspected by Scanning Electron Microscopy (SEM) and Energy Dispersive X-ray Diffraction (EDX). The stability of nickel oxide in the films was found to be enhanced against acidic environments. Electrochemical catalytic behavior of NiO<sub>x</sub> within the composite film was conserved and demonstrated by catalytic oxidation of methanol and ethanol.

**Keywords:** Nickel oxide · Polyaniline · Composite film · Electrocatalysis

## INTRODUCTION

Organic-inorganic composites have attracted considerable attention as they can combine the advantages of both components and may offer special properties through reinforcing or modifying each other [1]. Polyaniline (PAni) has been the subject of many studies due to its oxygen and moisture-stability and potential applications in many fields [2]. PAni can also provide good network for inorganic components and modify properties and stability of the latter [3]. Nickel oxide has received considerable attention due to potential applications in many fields such as electrochromics, electrocatalysis, supercapacitor etc [4–7]. Chemically synthesised PAni and NiO composite by Song and coworkers produced PAni / NiO nanoparticle, nanobelt, and nanotube in the presence of sodium dodecylbenzenesulfonate (SDBS). The composite materials showed improved conductivity and thermostability [8–10].

Electro-co-deposition is an effective way to make composite films with a large variety of tunable parameters and so has the advantage of convenient film control. Generally, PAni is synthesized by anodic polymerization of aniline in acidic aqueous solution [2]. Thus the electrochemical synthesis of organic-inorganic composites based on PAni and metal oxides are mostly conducted by selecting oxides which can be electrodeposited in low pH media [3, 11–13]. However, most oxides can only be electrodeposited from high pH media, which limits the formation of such PAni composites. Recently, we have demonstrated that it is feasible to form electroactive PAni in aqueous solutions of pH 2 to 12 [14]. PAni-SiO<sub>2</sub> and PAni-MnO<sub>x</sub> composites

were hence obtained [15, 16]. Nickel oxide was reported to be electrodeposited either at a fixed potential between 0.7 and 1.2 V or by dynamic potential cycling in the potential range of 0 ~ 1.2 V vs. SCE from Ni<sup>2+</sup> in neutral to weak basic solutions [17–22]. It is therefore likely that PANi and nickel oxide can be co-deposited to form an organic-inorganic composite film. In this paper, we report the electro-co-deposition of NiO<sub>x</sub> and PANi and the electrochemical activities of the obtained composite film through cyclic voltammetry. The morphologies and elemental components of the film were inspected by Scanning Electron Microscopy (SEM) and Energy Dispersive X-ray Diffraction (EDX), respectively. Film stability in acidic condition was investigated and the electrocatalytic property of the composite film was demonstrated.

## **EXPERIMENTAL**

### **Materials**

Aniline was distilled under vacuum before use. Other chemicals were of analytical grade and used as received. Electrochemical depositions were performed on electrochemical analyzer system, CHI 660B, on carbon cloth, using platinum plate and SCE as counter and reference electrode, respectively.

### **Synthesis of PANi-NiO<sub>x</sub> composite film**

Prior to electrodeposition, the carbon cloth was cleaned by acetone followed by distilled water. Electrochemical co-deposition of NiO<sub>x</sub> and PANi was carried out in a solution containing 0.2 M NiSO<sub>4</sub> and 0.005 M aniline adjusted to pH 7.3 by H<sub>2</sub>SO<sub>4</sub> or NaOH. Cyclic voltammetry (CV) with fixed scans (25 consecutive cyclic scans) between  $-0.3 \sim 1.2$  V vs. SCE at  $50 \text{ mV}\cdot\text{s}^{-1}$  were performed. Pure nickel oxide and PANi films were electrodeposited similarly.

### **PANi-NiO<sub>x</sub> film characterization**

Electrochemical activities of the films were studied by cyclic voltammetry at  $50 \text{ mV}\cdot\text{s}^{-1}$  in 0.1 M NaOH and 0.1 M H<sub>2</sub>SO<sub>4</sub> respectively. The morphologies of the film and the elemental components were inspected by Scanning Electron Microscopy (SEM) and Energy Dispersive X-ray Diffraction (EDX) on SHIMADZU SSX-550 Scanning Electron Microscope.

Stability of nickel oxide within the composite film in acidic solutions was investigated through cyclic voltammetry in 0.1 M NaOH at  $50 \text{ mV}\cdot\text{s}^{-1}$  after

immersion for 3 hours in H<sub>2</sub>SO<sub>4</sub> solutions of different pH (pH 1.0, 2.0, 2.5, 3.0, 3.5, 4.0). Electrochemical catalytic properties of the films were investigated by cyclic voltammetry at 5 mV·s<sup>-1</sup> in solution containing 1.0 M NaOH with different concentrations of MeOH and EtOH.

## RESULTS AND DISCUSSION

### Synthesis of PANi-NiO<sub>x</sub> composite film



Our previous work has shown that electroactive PANi film can be fabricated through electro-oxidative polymerization of aniline in aqueous solution at pH 2.0 to 12.0 [14]. Nickel oxide film can generally be obtained from neutral to weak basic solutions of Ni<sup>2+</sup> through similar electro-oxidation technique [17–21]. Thus, it is probable that PANi- nickel oxide composite film can be formed by electrochemical co-deposition from a single solution. Hence, by using a solution containing 0.2 M Ni<sup>2+</sup> and 0.005 M aniline adjusted to pH 7.3, a composite film was successfully deposited onto the carbon cloth electrode.

Figure 1 shows the cyclic voltammograms (CV) obtained during the deposition process. Initially, a clear oxidation peak showed up at around 1.1 V vs. SCE. After the first scan, this oxidation current appeared to be much smaller. This is due to a number of factors that include proton generation from aniline oxidation (Scheme 1) which significantly reduced the amount of hydroxyl ions available for the Ni<sup>2+</sup> oxidation [23, 24]; secondly, the electrode surface was being deactivated (partially blocked) by the presence of polyaniline (PANi) film that reduced the mass transport process. However, it was observed that the current density increased gradually with successive scans after the initial drop, indicating that oxidation of Ni<sup>2+</sup> still occurred readily but at a much slower rate on the electrode surface.


Similar conditions were used to deposit nickel oxide (NiO<sub>x</sub>) film. Figure 2 are the

CV scans obtained during the deposition process. An oxidation peak appeared at *ca.* 1.1 V initially, which increased in height with progressive scans and gradually shifted to *ca.* 1.2 V. Simultaneously, there was also a distinct reduction peak started at 0.65 V which increased in current density with successive scans and shifted down to 0.5 V.

The anodic electrochemical reactions are more complex but can be summarized as follows [25]:



Whereas the reduction reaction observed can be simplified as:



Equations 3-5 suggest that the product obtained was a mixture of NiO<sub>2</sub> and NiO-OH.

Both pure and composite films displayed characteristic NiO<sub>x</sub> electroactivities as previously reported for nickel oxides [5–7, 18] suggesting successful electro-co-deposition of PANi and NiO<sub>x</sub> from a single solution. Comparing the oxidation current densities from the two separate deposition processes that produced the composite film and the NiO<sub>x</sub> film, it was expected that there were much less NiO<sub>x</sub> deposited into the composite film. This is confirmed by the CV scans of the two materials presented in Figure 3 that shows, according the current density observed, the composite film is estimated to contain less than a tenth of NiO<sub>x</sub> compared to the pure NiO<sub>x</sub> membrane. However, this estimation can only be used as a general indication because the electron transfer efficiencies and inherent electrical resistance between the pure and composite films are expected to be quite different.

### **Characterization of PAni- NiO<sub>x</sub> composite film**

Elemental analysis of PAni-NiO<sub>x</sub> composite and nickel oxide films were carried out by Energy Dispersive X-ray Diffraction (EDX) technique. Similar spectra were obtained for the two films which identified the presence of more than one form of nickel oxides (Figure 4). Therefore a mixture of NiO<sub>2</sub> and NiO-OH may co-exist in the film according to equations 3-5. Scanning Electron Microscopy (SEM) images of the films revealed very different surface morphologies. PAni-NiO<sub>x</sub> composite adopted a much smoother morphology consisting of aggregations of sub micron particles; whereas the nickel oxide film was made up of much bigger worm like tubules several microns long (Figure 5). As shown in Figure 5a, nickel oxide particles are indistinguishable from that of the PAni, which may suggest they are well dispersed in polymer network of the composite film. This may explain why the  $\Delta E$  for Ni(II) / Ni(III) couple (shown in equation 3) obtained from the composite film is smaller than that obtained from the pure nickel oxide film as the fine dispersion of nickel oxide particle within the PAni network facilitates the electron exchange. However, the difference in  $\Delta E$  observed may also be attributable to an uncompensated resistance effect.

### **Electrochemical properties**

PAni-NiO<sub>x</sub> composite film displayed two pairs of redox peaks in 0.1 M H<sub>2</sub>SO<sub>4</sub> which were similar to a PAni film made under similar conditions (Figure 6). The first couple at *ca.* 0.2 V corresponded to the exchange between leucoemeraldine and emeraldine states of PAni. The second couple at *ca.* 0.4 V was related to the exchange between



emeraldine and pernigraniline [26]. However, these redox couples did not exist in alkaline solution as PANi was not electroactive under alkaline media (ca. pH > 10.0). Meanwhile, NiO<sub>x</sub> was unstable in acidic conditions as the compound dissolved relatively rapidly in acids. Figure 7 is a typical example of CVs obtained from a NiO<sub>x</sub> film at pH 2.1. The cathodic current reduced quickly with progressive scans and almost completely lost its activity after just 5 cycles. These contrasts in property had made the study of PANi-NiO<sub>x</sub> composite film more challenging as solutions of two extreme pHs had to be used to investigate the activities of PANi and NiO<sub>x</sub> components, i.e. acidic media for PANi and alkaline for NiO<sub>x</sub>.

By comparing the cathodic current of the composite film at 0.25 V vs. SCE to that of the pure nickel oxide film at 0.2 V vs SCE after 20 scan cycles, we have demonstrated that PANi-NiO<sub>x</sub> composite film has enhanced stability in acidic media (Figure 8). The modified electrodes were immersed in acidic solutions ranging from pH 4.0 to 1.0 for 3 hours before the cathodic current was measured in 0.1 M NaOH. Results show that significant electro-activity could be detected for PANi-NiO<sub>x</sub> composite films at low pHs as detailed in Figure 8. The data showed that above pH 2.5 the composite film remained electrochemically active and was relatively stable; whereas the pure NiO<sub>x</sub> film was only stabilised above pH 3.5. It was demonstrated that this simple technique for immobilization of nickel oxide into PANi matrix has resulted in a more stable material.

### **Catalytic properties**

It is known that nickel oxide is an electrocatalyst for hydroxylated organic compounds

[5, 6, 27, 28]. It is envisaged that this composite material may retain and enhance the catalytic properties of the nickel oxide through fine dispersion of the catalyst particles into the conductive PANi matrix to result in a drastic increase in surface area. Additionally, the conductive PANi matrix, being closely associated to the nickel oxide catalyst as a result of co-deposited film, is expected to facilitate electron transfer during the electrocatalytic reaction. These effects were demonstrated in the catalytic oxidation of alcohols in alkaline media.

Figure 9 and 10 were data obtained during the electro-oxidation of methanol and ethanol respectively monitored by cyclic voltammetry. On addition of the substrates, large anodic current increases appeared above 0.3 V (*vs.* SCE) which was corresponding to the Ni(II) to Ni(III) transition, indicating that electro-catalytic oxidation of the alcohols had occurred. The catalytic anodic reactions are summarized as follows:




Figure 11 presents two very similar calibration plots using the data shown in figures 9 and 10 which show that the composite film exhibited very high catalytic efficiency for methanol and ethanol oxidation. Given that only small amount of nickel oxide catalyst was present in the composite film, very fast mass transport and efficient electron transfer must have achieved to produce the observed catalytic behavior.

These data also indicate that the composite film may offer an electrochemical way of detecting alcohols in aqueous media across a broad concentration range of ca. 2 mM to 400 mM. Detail sensing investigation is beyond the scope of this work and

will be discussed elsewhere.

We have reported the synthesis and characterization of PANi-NO<sub>x</sub> composite film. This composite material is stable in pH >2.5 and in basic environments and remains electrochemical active. The distinct physical configuration of the composite has led to enhanced catalytic properties which may have good potential in application areas such as electrocatalysis, sensing, and fuel cell etc.

## CONCLUSIONS

PAni-NiO<sub>x</sub> composite film was obtained through cyclic voltammetric technique in the solution containing 0.2 M NiSO<sub>4</sub> and 0.005 M aniline at pH 7.3. The cyclic voltammogram (CV) of the composite film displayed well-defined anodic and cathodic peaks associated with Ni(II) / Ni(III) redox couple in 0.1 M NaOH, which was similar to that of nickel oxide film. Nickel oxide particles were well dispersed in polymer network of the composite film and was witnessed by the facilitated Ni(II) / Ni(III) redox transition, enhanced catalytic activities and increased NiO<sub>x</sub> stability within the composite material.

## **Acknowledgments**

We gratefully acknowledge financial support from National Natural Science Foundation of China (project number: 50372011), Natural Science Foundation of Liaoning Province, China (project number: 20052016) and the China-Ireland Collaboration Funding (co-funded by SFI, RCS and CMOST). The author (K Lau) also wishes to thank DCU fellowship award for financial support.

## REFERENCE

1. Pedro G-R (2001) *Adv Mater* 13: 163
2. Subramania A, Devi S-L (2008) *Polym Adv Technol* 19: 725
3. Shen P-K, Huang H-T, Tseung A-C-C (1992) *J Electrochem Soc* 139:1840
4. Karlsson J, Roos A (2000) *Solar Energy* 68: 493
5. Berchmans S, Gomathi H, Rao G-P (1995) *J Electroanal Chem* 394: 267
6. Cataldi T-R-I, Centonze D (1995) *Anal Chim Acta* 307: 43
7. Nam K-W, Yoon W-S, Kim K-B (2002) *Electrochim Acta* 47: 3201
8. Song G-P, Bo J, Guo R (2005) *Colloid Polym Sci* 283: 677
9. Song G-P, Han J, Guo R (2007) *Synth Met* 157: 170
10. Han J, Song G-P, Guo R (2006) *J Polym Sci, Part A: Polym Chem* 44: 4229
11. Sun L-J, Liu X-X (2008) *Eur Polym J* 44: 219
12. Liu X-X, Bian L-J, Zhang L, Zhang L-J (2007) *J Solid State Electrochem* 11: 1279
13. Hu C-C, Chu C-H (2000) *Mater Chem Phys* 65: 329
14. Liu X-X, Zhang L, Li Y-B, Bian L-J, Su Z, Zhang L-J (2005) *J Mater Sci* 40: 4511
15. Liu X-X, Zhang L, Li Y-B, Bian L-J, Huo Y-Q, Su Z (2006) *Polym Bull* 57: 825
16. Sun L-J, Liu X-X, Lau K-K-T, Chen L, Gu W-M (2007) *Electrochim Acta* 53: 3036
17. Casella I-G, Spera R (2005) *J Electroanal Chem* 578: 55
18. Tench D, Warren L-F (1983) *J Electrochem Soc* 130: 869

19. Prasad K-R, Miura N (2004) *Appl Phys Lett* 85: 4199
20. Chigane M, Ishikawa M (1992) *J Chem Soc Faraday Trans* 88: 2203
21. Yang M-C, Lin C-K, Su C-L (1995) *J Electrochem Soc* 142: 1189
22. Peng X-Y, Li W, Liu X-X, Hua P-J (2007) *J Appl Polym Sci* 105: 2260
23. Gospodinova N, Terlemezyan L (1998) *Prog Polym Sci* 23: 1443
24. Duic L, Mandic Z, Kovac S (1995) *Electrochim Acta* 40: 1681
25. Jayashree R-S, Kamath P-V (2001) *J Power Sources* 93: 273
26. Huang W-S, Humphrey B-D, MacDiarmid A-G (1986) *J Chem Soc Faraday Trans*  
82: 2385
27. George M-V, Balachandran K-S (1975) *Chem Reviews* 75: 491
28. Casells I-G, Cataldi T-R-I, Salvi A-M, Desimoni E (1993) *Anal Chem* 55: 3143

## FIGURE CAPTIONS

- Figure 1** Cyclic voltammograms obtained for the electro-co-deposition of composite film on carbon cloth from a solution containing 0.2 M  $\text{Ni}^{2+}$  and 0.005 M aniline (pH = 7.3). Scan rate:  $50 \text{ mV s}^{-1}$ .
- Figure 2** Cyclic voltammograms obtained for the electrodeposition of nickel oxide on carbon cloth from a solution of 0.2 M  $\text{Ni}^{2+}$  (pH = 7.3). Scan rate:  $50 \text{ mV s}^{-1}$ .
- Figure 3** Cyclic voltammograms of PANi- $\text{NiO}_x$  (a: solid line) and similarly prepared nickel oxide (b: dash line) films in 0.1 M NaOH. Scan rate:  $50 \text{ mV s}^{-1}$ .
- Figure 4** EDX spectra of (a) PANi- $\text{NiO}_x$  and (b)  $\text{NiO}_x$ .
- Figure 5** SEM images of (a) PANi- $\text{NiO}_x$  composite and (b) similarly prepared nickel oxide films.
- Figure 6** Cyclic voltammograms of PANi- $\text{NiO}_x$  (solid line) and similarly prepared PANi (dash line) films in 0.1 M  $\text{H}_2\text{SO}_4$ . Scan rate:  $50 \text{ mV s}^{-1}$ .
- Figure 7** Cyclic voltammograms of  $\text{NiO}_x$  film in  $\text{H}_2\text{SO}_4$  solution at pH 2.1. Scan rate:  $50 \text{ mV s}^{-1}$ . a - e: cycles 1 to 5 showing progressive reduction in current density.
- Figure 8** Normalized Percentage cathodic current density obtained after 20 scan cycles in 0.1 M NaOH for (a) nickel oxide (solid triangle) and (b) the PANi- $\text{NiO}_x$  composite (open circle) after the electrodes were immersed for 3 hours in various  $\text{H}_2\text{SO}_4$  solutions of pH 1 to 4. ( $i_c$ ) and ( $i_c'$ ) denotes



current obtained before and after acid immersion. Peak currents were obtained at 0.2 V and 0.25 V vs. SCE for nickel oxide and PANi-NiO<sub>x</sub> composite films respectively.

**Figure 9** Cyclic voltammograms of PANi-NiO<sub>x</sub> composite film in 1.0 M NaOH and different concentrations of methanol. Scan rate: 5 mV s<sup>-1</sup>; concentration of methanol: a: 0 M, b: 0.006 M, c: 0.01 M, d: 0.02 M, e: 0.04 M, f: 0.2 M, g: 0.4 M, h: 0.6 M, i: 0.8 M, j: 1.0 M.

**Figure 10** Cyclic voltammograms of PANi-NiO<sub>x</sub> composite film in 1.0 M NaOH and different concentrations of ethanol. Scan rate: 5 mV s<sup>-1</sup>; concentration of ethanol: a: 0 M, b: 0.02 M, c: 0.06 M, d: 0.08 M, e: 0.2 M, f: 0.4 M, g: 0.6 M, h: 0.8 M, i: 1.0 M.

**Figure 11** Calibration plot for the electrocatalytic oxidation of methanol (a: open square) and ethanol (b: solid triangle) on the PANi-NiO<sub>x</sub> composite film.

**Scheme 1** Electro-polymerization of aniline showing protons being generated during the anodic oxidation process.